



ROOF DETAILS WATERPROOFING



MARISEAL DETAIL

ROOF DETAILS WATERPROOFING

MARISEAL • DETAIL

The **MARISEAL** *DETAIL* is a liquid-applied, thixotropic, permanent elastic, **fiber-reinforced**, one component polyurethane coating used for long-lasting waterproofing of complex roofing details and connections.




waterproof details like:

- Pipes
- Flashings and 90° angles
- Lightdomes
- Chimneys
- Photovoltaic systems
- Wall-floor connections
- Gutters, etc.











advantages

- simple application (brush)
- fiber reinforced
- it forms seamless membrane without joints or leak possibilities
- resistant to water, rain and frost
- maintains its mechanical properties over a temperature span of -30°C to +80°C
- provides water vapor permeability
- full surface adherence without any additional anchoring
- in case of damage, membrane can be easily repaired locally within minutes
- low cost

The **MARISEAL • DETAIL SYSTEM**

consists of the compatible components:

- MARISEAL DETAIL
- **MARISEAL DETAIL** REINIGER (CLEANER)
- MARISEAL DETAIL PRIMER
- MARIFLEX PU30 SEALANT



The **MARISEAL DETAIL** can be used on:



Beton



Mineral finished bitumenfelt



Metal



Mortar



Plain Bitumenfelt



PVC and Aluminium profile



Brick



PVC and EPDM membrane



Wood, etc

example I: Lightdome



Mask the area to be waterproofed, with a masking tape in a sufficient size. Prepare the surface according to the surface preparation table.



Apply the second layer of MARISEAL DETAIL thickly with a flat brush and remove masking tape.

example 2: Pipe Penetration



Mask the area to be waterproofed, with a masking tape in a sufficient size. Prepare the surface according to the surface preparation table.



Apply the second layer of MARISEAL DETAIL thickly with a flat brush and remove masking tape.



Apply the first layer of MARISEAL DETAIL with a flat brush and spread evenly.



If desired, for aesthetic reasons, slate chippings can be sprinkled in the wet coating in excess. Apply slight pressure by hand to stabilize the slate chippings.



Apply the first layer of MARISEAL DETAIL with a flat brush and spread evenly.



If desired, for aesthetic reasons, slate chippings can be incorporated in the coating in excess.

Important

| Surface preparation: | | Primer not necessary | MARISEAL DETAIL PRIMER recommended |
|--|--------|----------------------|---------------------------------------|
| Polymeric Bitumenfelt (APP/SBS) | *5 | × | |
| Chippings finished Bitumenfelt (APP/SBS) | *4 | × | |
| Chippings finished Oxidized Bitumenfelt | *4 | × | |
| Plain Oxidized Bitumenfelt | *5 | × | |
| Painted surfaces | *3 | × | |
| Steel | *I, *3 | × | |
| Aluminium | *I, *3 | × | |
| Copper | * | × | |
| Zinc | * | × | |
| Concrete | *2, *6 | | × |
| Lightweight concrete | *2, *6 | | × |
| Plaster | *2, *6 | | × |
| Screed | *2, *6 | | × |
| Brick | *2, *6 | | × |
| Stones | *2, *6 | | × |
| EPDM membranes | *I, *7 | × | |
| PVC membranes | *1, *7 | × | |
| PVC rigid | * | × | |
| Wood | *2 | | × |
| Polyester | *I, *7 | × | |
| Acrylic glass | * | × | |
| Glass | * | × | |

*I: Before application, grind surface with sandpaper or grinding wheel. Then thoroughly clean/ degrease with MARISEAL DETAIL CLEANER.

*2: Residual moisture content of mineral substrates max. 5%. New cementitious surfaces must be at least 28 days old. Remove loose pieces mechanically.

*3:Always remove old paints.

*4: MARISEAL DETAIL PRIMER binds the slate chippings on the bitumenfelt. If in doubt it is recommended to use the MARISEAL DETAIL PRIMER.

*5: Liquify surface by firetorch and immediately saturate with enough dry silica sand (0.4-0.8mm).*6: Before coating, brush off the surface with a wire brush, to roughen it.

*7: Always perform adhesion test before application For not listed substrates please contact MARIS POLYMERS application department.

All information regarding the treatment of surfaces is to be considered indicative, as corresponds to the current level of laboratory and practical experience. Given the multitude of different materials in the market, deviations are possible. Therefore, absolute accuracy of given information can not be guaranteed. Due to the different object requests and the varying conditions, an adhesion test is necessary to guarrantee suitability for the specific purpose. Preliminary coating adhesion tests are therefore recommended in all cases. Should doubts arise about the suitability of the coating for your surface, we will gladly test your surface samples.

Product information:

| MARISEAL DETAIL | | | | | |
|-----------------|--|---|--|--|--|
| Description | One component, polyurethane-based, liquid membrane, reinforced with synthetic fibers | | | | |
| Packaging | supplied in 6 kg pails | | | | |
| Properties | Color Density Hardness (Shore A scale) Viscosity Elongation at Break Tensile strength Rain stability time (20 ^o C) Light pedestrian traffic Final Curing time | Grey, Black I.32 g/cm3 70 Thixotropic >250% >4 N/mm2 3-4 Hours I2-18 Hours 7 Days | | | |

| MARISEAL DETAIL PRIMER | | | | | | |
|------------------------|--|---------------------------------|--|--|--|--|
| Description | One-component, quick drying, polyurethane-based primer | | | | | |
| Packaging | supplied in Ikg pails | | | | | |
| Properties | Color Density Hardness Shore A | Transparent I.0 g/cm3 >95 | | | | |
| | Adhesion (Concrete) Touch dry (20 ⁰ C) | >1.5 N/mm2 1-2 Hours | | | | |

Safety measures: contains isocyanates. See information supplied by the manufacturer. Please study the Safety Data sheet.